

Zirconia (ZrO2)

Performance parameters of zirconia

Material Properties	Unit	Zirconia
Density	g/cm³	6.02
Vickers hardness	GPa	13
Bending strength	MPa	900
Compressive strength	MPa	2400
Elastic modulus	GPa	210
Toughness	MPa·m ^{1/2}	7
Poisson's ratio	—	0.31
Young's Modulus	GPa	200

Thermal Properties	Unit	Zirconia
Thermal conductivity	W/mK	3
melting point	°C	2700
Maximum operating temperature	°C	1000
linear expansion coefficient	10 ⁻⁶ /K	10



Electrical Properties	Unit	Zirconia
Dielectric constant	1 MHz	20-30
Breakdown voltage	kV/mm	10-30
Resistivity	Ω·cm	10 ^{^5}

Note: This value is for reference only and may vary slightly depending on the batch conditions.

Jundro Ceramics is a global material manufacturer that offers a wide range of advanced materials
We produce high-quality and complex products, providing significantly enhanced performance for customers engineering.
Our comprehensive service range includes material selection, precision machining, surface treatment, and quality testing to ensure that each product can perform its best practical applications.

DONGGUAN JUNDRO CERAMICS TECHNOLOGY CO.LTD

Add: Room 306, Gate B, Unit 1, Block 2 South, No. 1 Yile Road, Songshan Lake, Dongguan City, Guangdong Province, China(523808)